

The Characterization of Natural Zeolite For Water Filtration System

¹Mirzan T. Razzak, ²Thamzil Las, ¹Priyambodo

¹) Center for Integrated Laboratory, ²) Faculty of Science and Technology
State Islamic University of Syarif Hidayatullah Jakarta

Abstract

The characterization of Indonesian's natural zeolite for water purification using X-Ray Diffractometer has been done. The objective is to obtain a general guidance for development of natural zeolite in molecular sieve, ion exchange and catalyst applications. It was found that the XRD spectra show two zeolite types. The zeolites originated from Lampung (ZL) was belong to clinoptilolite group and that originated from Banten (ZB) was belong to mordenite group. The crystal system for ZL was monoclinic with end-centered lattice and space group of Cm/2 (12). The crystal system for ZB was orthorhombic with end-centered lattice and space group of Cmc21 (36). The character of both zeolites were confirm by ICDD standard library. It was also found that the particle size of zeolites did not affect the XRD spectra where zeolite of 40-50 mesh was similar to that XRD spectra of zeolite of 170-200 mesh. The chemical analyses show that both zeolites contain almost similar chemical elements. The contents of Fe, Ca, and K were found higher in ZL as it is compared to ZB. Reciprocally, Na was found higher in ZB. The water filtration ability shows that ZB was better than ZL for filtering of Pb and Fe elements. These ability were improved by chemical activation of zeolites. These two zeolites, however, behave similar less ability for the filtering of Ca and Mg elements. These characterization is necessary to designing a further development of natural zeolite applications.

Keywords: natural zeolite, clinoptilolite, mordenite, x-ray diffraction, water filter

Abstrak

Telah dilakukan karakterisasi zeolit alam Indonesia untuk pembuatan sistem penjernihan air. Zeolit alam yang didapat dari Lampung (ZL) dan Banten (ZB) dikarakterisasi dengan X-Ray Diffractometer (XRD) dan diuji kemampuannya untuk penjernihan air. Tujuan penelitian ini adalah untuk mengembangkan pemanfaatan zeolit alam sebagai penyaring (molecular sieve), penukar ion maupun sebagai katalis. Pengukuran XRD menunjukkan bahwa zeolit alam yang berasal dari Lampung termasuk jenis klinoptilolit dengan sistem kristal monoklinik, jenis kisi end-centered, dan group Cm/2 (12). Sedangkan yang berasal dari Banten termasuk jenis mordenit dengan sistem kristal orthorhombic, jenis kisi end-centered, dan group Cmc21 (36). Dari penelitian ini, diketahui juga bahwa ukuran zeolit alam tidak mempengaruhi bentuk pola spektrum XRD. Analisa kimia menunjukkan bahwa kedua jenis zeolit tersebut mengandung unsur kimia yang sama. Kadar unsur Fe, Ca, dan K didapatkan lebih tinggi terkandung dalam ZL. Sebaliknya kadar unsur Na lebih tinggi dalam ZB. Kemampuan penyaringan Pb dan Fe didapatkan lebih baik pada ZB. Kemampuan ini dapat ditingkatkan bila zeolit terlebih dahulu diaktivasi secara kimia. Namun demikian baik ZL maupun ZB mempunyai kemampuan penyaringan Ca dan Mg yang sangat rendah. Karakteristik ini sangat berguna untuk perancangan dan pengembangan aplikasi ZL dan ZB ke depan.

Kata kunci: zeolit alam, klinoptilolit, mordenit, difraksi sinar-x, filter air

1. INTRODUCTION

Indonesia is carrying out different research work in order to improve the natural resources utilization. It was understood that the

higher utilization of natural resources make higher contribution to natural development. In this work, natural zeolites which are abundance available in Indonesian wish to be developed to

achieve a more added value materials such as water purification/filtration system.

In fact, the natural zeolites have been used in agriculture as soil conditioner, as component of fertilizer, animal feed as well as a neutralization agent for bad smell waste [1,2]. The applications of zeolite in engineering are still very few. Some research were done to develop zeolites for its application as water filtration or as membrane system [3,4,5,6].

According to various researches, zeolite mainly a synthetic ores may have a great potential as membrane system such as micro filtration (MF), ultra filtration (UF), ad reverse osmosis (RO) as well as a powerful catalyst, ion exchanger, and gas separation systems [7,8,9,10,11,12,13].

In fact, however the researches for the utilization of natural zeolites are still low due to some reasons. Among of that reasons were the variety of character of natural zeolites. Two sources of natural zeolite, i.e. originated from Lampung (ZL) and originated from Bayah, Banten (ZB) are used to be characterization in the present work. The characterizations of two zeolites were carried out using x-ray diffractometer (XRD) instrument.

The objectives of this work is to obtain a general orientation of zeolite's crystal system, its properties as well as to determine a selective elements that probably affecting in the character of natural zeolite for its application as water filtration system.

2. MATERIALS AND METHOD

Materials

Natural zeolite were supplied by PT Minamata Mineral Perdana, i.e. originated from Lampung (ZL), and by volunteer zeolite mining agency, i.e. originated from Bayah, Banten (ZB). The zeolites were treated by ball milling and sieved to obtain a homogeneous powder size of 40-200 mesh, before used. Some necessary chemicals were used as a zeolite binder or as chemical activation agent.

Instruments

Shimadzu X-Ray Diffractometer instrument type 7000 made in Japan was used to

characterization of crystal system. The instrument was first calibrating using silicon standard.

Perkin Elmer Atomic Absorption Spectrometer (AAS) type AAnalyst 700, made in USA was used to analyze chemical elements. Other equipments such Memmert Oven (Germany) and Vulcon Kiln type 550 (Germany) were used for drying and sintering work. Various tools, beaker glass and plastic equipments were used as necessary.

Zeolite Activation

The chemical activation of zeolite were done as follows:

50 gr of zeolites was kept in HCl 2M solution for one hour, washed and decanted by aquadest until neutral (pH=7.0). It was, they kept in NaNO₃ 2M solution for 1 hour, washed and decanted adequately by aquadest until neutral, and then dried in oven at 105°C until a constant weight.

XRD Characterization

Natural zeolite powder sample was put into a sample holder appropriately, kept homogeneous surface and placed it at measurement position. The measurement was done according to computer operating system and the obtained XRD spectrum was recorded. It took about 45 minute for each sample measurement. The obtained XRD spectrum was evaluated by standard diffraction data of x-ray from ICDD (International Centre for Diffraction Data).

AAS Measurement

0.5 gr of zeolite sample was destructed by aqua regia (HCl + HNO₃), diluted to 100 ml by distilled water and arrange the concentration to be appropriate for AAS measurement. The measurement was done by flame detector technique and the results were computerized recorded and print-out as necessary.

Filter Preparation

The zeolite sample was poured into a glass column (dia.3cm) for 5 cm thickness for media zeolite bed. The zeolite sample may be 40-200 mesh zeolite powder or a chemical

activation zeolite. The media zeolite bed ability in filtering of different solution of Pb acetate (0.2 M), FeCl₃ (0.1 M), MgSO₄ (1.0 M), and CaCl₂ (0.2 M) were observed. The filtrate was measured by AAS after a necessary dilution. The contents of Pb, Fe, Mg, and Ca either in filtrate and remain in media zeolite bed was evaluated. The filtering capability of natural zeolite that was prepared by a binder was also investigated.

3. RESULTS AND DISCUSSION

XRD of Lampung Zeolite (ZL)

Figure 1 shows the XRD Spectrum of Lampung zeolite. As can be seen in Fig.1, there are 3 strongest peaks, followed by another 3 weaker peaks. The position of the six peaks can be summarized in Fig. 2, and it details can be seen in Table 1.




Fig.1. XRD Spectrum of Lampung Zeolit.




Fig.2. XRD Spectrum Line of Lampung Zeolit

Tabel 1. The Strongest Peaks of XRD Spectrum of Lampung Zeolite (Powder)

*** Basic Data Process ***

Group : Zeolit
Data : Natural Powder

#	Strongest 3 peaks						
no.	peak no.	2Theta (deg)	d (Å)	I/I1	FWHM (deg)	Intensity (Counts)	Integrated Int (Counts)
1	45	27.9583	3.18874	100	0.10640	715	4385
2	29	22.3963	3.96647	54	0.29840	388	6224
3	9	9.8631	8.96057	39	0.21860	282	3110

According to ICDD 47-1870 data library, the existence of the strongest peaks may indicate that the mineral was appropriate with potassium sodium calcium aluminum silicate hydrate of clinoptilolite-Na.

Based on Bravais classification crystal system, it was found to be a base-centered monoclinic, with a lattice of end-centered and the space group of C2/m (12). Accordingly, there are three unequal axes, one pair not at right angle, $a \neq b \neq c$, $\alpha = \gamma = 90^\circ$ and $\beta \neq 90^\circ$ [14]. The crystal system can be illustrated as the following figure (See Fig.3).




Fig.3. Bravais lattice for monoclinic crystal system.

Tabel 2. ICDD Data for 47-1870

ICDD 47-1870

Mineral : Clinoptilolite-Na

Potassium Sodium Calcium Aluminum Silicate Hydrate

Chemical : $[\text{Na}, \text{K}, \text{Ca}]_5 \text{Al}_6 \text{Si}_{30} \text{O}_{72} \cdot 18 \text{H}_2\text{O}$

Crystal System	Monoclinic	Space Group	C2/m (12)	a	17,647	α	90
Lattice	End-centered	Density	2.046	b	18,007	β	116.3
Lambda	1,5406	Pattern	I	c	7,396	γ	90

It can be concluded therefore, that the observed zeolite (ZL) should be a clinoptilolite with a monoclinic crystal system.

Further XRD measurement of ZL with

The data indicate that the crystal structure should belong to a clinoptilolite, its density of 2.16 g/mol and a unit cell volume of 2100Å. These agreed to description that was reported by Thamzil Las (Ph.D. Thesis) [15]. The unit cell may have a dimensions of $a=7.41 \text{ \AA}$, $b=17.89 \text{ \AA}$, and $c=15.85 \text{ \AA}$. If the data are compared to that ICDD library, then it seems to be the same. In other word, the ZL could be predicted behave a crystal structure belong clinoptilolite group. The chemical formula of clinoptilolite is assumed to be $\text{Na}_6 [(\text{AlO}_2)_6 (\text{SiO}_2)_{30}] 24 \text{H}_2\text{O}$.

In ICDD 47-1870 data, the clinoptilolite-Na may contains of $[\text{Na}, \text{K}, \text{Ca}]_5 \text{Al}_6 \text{Si}_{30} \text{O}_{72} \cdot 18 \text{H}_2\text{O}$ as can be seen in Table 2.

different mesh has shown the same pattern of XRD spectrum. The strongest peaks was given at 2θ of 28.0520° followed by the second strongest at 2θ of 22.3963° . (See Table 3)

Tabel 3. The Strongest Peaks of XRD Spectrum of Lampung Zeolite (60-100 mesh)

Group : Zeolit
Data : 60_100 Mesh

# Strongest 3 peaks							
no. peak	no.	2Theta (deg)	d (Å)	I/I1	FWHM (deg)	Intensity (Counts)	Integrated Int (Counts)
1	55	28.0520	3.17830	100	0.10620	677	4102
2	39	22.3934	3.96698	35	0.32680	234	3638
3	38	22.0178	4.03380	29	0.15410	197	1279

From Table 3, the peaks of XRD spectrum at 2θ of 28.0520° and 22.3963° may be estimated as peaks character for natural zeolite of ZL. In fact, the XRD spectrum of ZL do not affected by the particle size, since the two XRD spectrum of ZL show the similar pattern.

XRD of Activated Lampung Zeolite (ZL)

Fig. 4 shows the XRD spectrum of activated zeolite ZL. As can be seen in Fig. 4, there are three other strong peaks i.e. at 2θ of 42.2126° , 31.4545° , and 51.4774° beside of three peaks that were assumed to be

characterization's peaks of clinoptilolite. Actually, the three other strong peaks have also available in XRD spectrum pattern of previously ZL, but in the form of weaker peaks.

Perhaps a higher peak at 2θ of 42.2126° as its compared to that previously ZL was caused by sodium cation that coming from activation process. If it's true, it can be predicted that activated ZL may containing a single cation of Na. Therefore, the activation of zeolite can be favorable for molecular siever as well as for cation exchanger.




Fig.4. XRD spectrum of activated Lampung zeolit.

Perhaps a higher peak at 2θ of 42.2126° as its compared to that previously ZL was caused by sodium cation that coming from activation process. If it's true, it can be predicted that

activated ZL may containing a single cation of Na. Therefore, the activation of zeolite can be favorable for molecular siever as well as for cation exchanger.




Fig.5. XRD Spectrum of Bayah, Banten Zeolit (40-50 mesh)

Fig. 5 shows the XRD spectrum of Bayah, Banten zeolite (ZB) of particle size of 40-50 mesh. As can be seen in Fig.5, there are three strongest peaks available i.e. peak at 2θ of 25.6897° (100), 27.3619° (95), and 26.6704°

(77). Other strong peaks were shown at 2θ of 27.7185° (68), 9.8023° (62), and 13.6000° (51). All the peaks may be assumed as a characteristic XRD spectrum of ZB. Detail data of XRD spectrum of ZB are presented in Table 4.

Tabel 4. The Strongest Peaks of XRD Spectrum of Bayah, Banten Zeolite (40-50 mesh)

```

*** Basic Data Process ***
Group      : Zeolit
Data       : 40_50 Mesh

# Strongest 3 peaks
no. peak  2Theta (deg)  d (A)  I/I1  FWHM (deg)  Intensity (Counts)  Integrated Int (Counts)
1         46         25.6897  100   0.24540     598                9606
2         39         27.3619   95   0.41990     567                10712
3         49         26.6784   77   0.37920     462                9189

# Peak Data List
no. peak  2Theta (deg)  d (A)  I/I1  FWHM (deg)  Intensity (Counts)  Integrated Int (Counts)
1         5.4600       16.17276  5     0.24000     30                 466
2         5.8200       15.17317  5     0.24000     30                 475
3         6.3000       14.01815  3     0.11340     19                 118
4         6.5213       13.54293  5     0.26930     32                 443
5         6.5213       13.54293  5     0.26930     32                 443
6         6.5800       13.30000  9     0.28000     18                 321
7         6.5800       13.30000  9     0.28000     18                 321
8         6.5800       13.30000  9     0.28000     18                 321
9         6.5800       13.30000  9     0.28000     18                 321
10        6.5800       13.30000  9     0.28000     18                 321
11        6.5800       13.30000  9     0.28000     18                 321
12        6.5800       13.30000  9     0.28000     18                 321
13        6.5800       13.30000  9     0.28000     18                 321
14        6.5800       13.30000  9     0.28000     18                 321
15        6.5800       13.30000  9     0.28000     18                 321
16        6.5800       13.30000  9     0.28000     18                 321
17        6.5800       13.30000  9     0.28000     18                 321
18        6.5800       13.30000  9     0.28000     18                 321
19        6.5800       13.30000  9     0.28000     18                 321
20        6.5800       13.30000  9     0.28000     18                 321
21        6.5800       13.30000  9     0.28000     18                 321
22        6.5800       13.30000  9     0.28000     18                 321
23        6.5800       13.30000  9     0.28000     18                 321
24        6.5800       13.30000  9     0.28000     18                 321
25        6.5800       13.30000  9     0.28000     18                 321
26        6.5800       13.30000  9     0.28000     18                 321
27        6.5800       13.30000  9     0.28000     18                 321
28        6.5800       13.30000  9     0.28000     18                 321
29        6.5800       13.30000  9     0.28000     18                 321
30        6.5800       13.30000  9     0.28000     18                 321
31        6.5800       13.30000  9     0.28000     18                 321
32        6.5800       13.30000  9     0.28000     18                 321
33        6.5800       13.30000  9     0.28000     18                 321
34        6.5800       13.30000  9     0.28000     18                 321
35        6.5800       13.30000  9     0.28000     18                 321
36        6.5800       13.30000  9     0.28000     18                 321
37        6.5800       13.30000  9     0.28000     18                 321
38        6.5800       13.30000  9     0.28000     18                 321
39        6.5800       13.30000  9     0.28000     18                 321
40        6.5800       13.30000  9     0.28000     18                 321
41        6.5800       13.30000  9     0.28000     18                 321
42        6.5800       13.30000  9     0.28000     18                 321
43        6.5800       13.30000  9     0.28000     18                 321
44        6.5800       13.30000  9     0.28000     18                 321
45        6.5800       13.30000  9     0.28000     18                 321
46        6.5800       13.30000  9     0.28000     18                 321
47        6.5800       13.30000  9     0.28000     18                 321
48        6.5800       13.30000  9     0.28000     18                 321
49        6.5800       13.30000  9     0.28000     18                 321

```

peak no.	2Theta (deg)	d (Å)	I/I1	FWHM (deg)	Intensity (Counts)	Integrated Int (Counts)
50	26.9000	3.31174	37	0.00000	223	0
51	27.1400	3.28300	26	0.29660	158	3356
52	27.7185	3.21578	68	0.39370	407	7308
53	28.1200	3.17077	25	0.29840	150	2474
54	28.5771	3.12108	11	0.21580	67	699
55	28.9218	3.08466	7	0.36360	44	740
56	29.5800	3.01751	4	0.12000	23	212
57	29.9533	2.98074	33	0.36670	199	3591
58	30.3600	2.94173	7	0.16000	43	585
59	30.9271	2.88907	22	0.27580	131	1869
60	31.9783	2.79646	19	0.23420	113	1387
61	32.3622	2.76416	3	0.07560	20	93
62	32.7636	2.73120	9	0.31270	54	960
63	33.2928	2.68899	4	0.34570	25	469
64	34.4414	2.60190	6	0.15710	33	298
65	34.7200	2.58165	11	0.16000	63	1343
66	35.0600	2.55739	13	0.00000	75	0
67	35.2600	2.54334	10	0.00000	59	0
68	35.6290	2.51784	18	0.33800	106	2145
69	36.1000	2.48607	6	0.26800	38	499
70	36.5800	2.45454	10	0.52000	61	1272
71	37.0000	2.42764	11	0.28660	64	972
72	37.6340	2.38818	4	0.17200	21	231
73	38.2353	2.35200	3	0.26070	18	290
74	39.4493	2.28237	6	0.20530	37	427
75	40.3950	2.23109	5	0.29000	27	469
76	41.6551	2.16646	8	0.20170	46	592
77	41.9512	2.15185	5	0.13750	27	207
78	42.2400	2.13781	4	0.13600	26	180
79	42.4650	2.12700	9	0.31000	51	650
80	42.7200	2.11489	4	0.12000	22	157
81	44.0766	2.05289	4	0.27330	21	411
82	44.9573	2.01470	10	0.29740	58	947
83	45.6725	1.98480	5	0.21500	30	357
84	45.9000	1.97549	5	0.26000	27	281
85	46.2000	1.96336	5	0.22660	32	290
86	46.4200	1.95457	8	0.42400	48	950
87	46.8000	1.93958	5	0.00000	29	0
88	47.0483	1.92992	6	0.20330	36	595
89	48.4315	1.87798	9	0.27190	55	881
90	50.0600	1.82064	8	0.21140	50	530
91	50.3200	1.81184	6	0.21500	38	471
92	50.8984	1.79260	12	0.25190	74	1148
93	53.4125	1.71400	5	0.20500	32	414
94	53.8000	1.70257	3	0.32000	19	374
95	54.0000	1.69673	4	0.00000	23	0
96	54.1950	1.69109	6	0.23000	34	528
97	55.2571	1.66107	6	0.23430	36	643
98	55.6566	1.65009	4	0.23330	23	347
99	56.9650	1.61526	5	0.17000	28	311
100	57.8200	1.59339	6	0.22000	37	536
101	59.8000	1.54527	5	0.28000	31	461
102	59.9800	1.54107	4	0.28000	25	369
103	60.2400	1.53503	3	0.00000	20	0
104	60.5200	1.52860	4	0.00000	26	0
105	60.7800	1.52268	8	0.36000	47	631
106	60.9400	1.51907	5	0.29720	32	325
107	61.3672	1.50951	3	0.08780	18	101
108	61.6318	1.50367	7	0.20640	44	422
109	61.9400	1.49692	6	0.28000	50	825
110	62.2800	1.48956	4	0.00000	24	0
111	62.5200	1.48442	4	0.00000	21	0

The measurement of XRD spectrum of ZB for different particle size of 170-200 mesh results the same XRD spectrum pattern. The XRD spectrum of ZB which has particle size of 170-200 mesh shows three strongest peaks at 2θ of 25.780° (100), 22.382° (78), and 9.761° (54) and

these similar to that XRD spectrum of other particle size of ZB. Therefore, the particle size of zeolite may concluded do not affect the pattern of XRD spectrum. Table 5 shows ICDD data for 49-0924

Tabel 5. ICDD Data for 49-0924

ICDD 49-0924

Mineral : Mordenite, syn

Sodium Aluminum Silicate – Zeolite Al-mordenite

Chemical : $\text{Na}_2 \text{Al}_2 \text{Si}_{13,3} \text{O}_{29,6} + x$

Crystal System	Orthorhombic	Space Group	Cmc21 (36)	a	18,067	α	90
Lattice	End-centered	Density	-	b	20,284	β	90
Lambda	1,5406	Pattern	I	c	7,491	γ	90

If the XRD peaks of ZB is compared to that ICDD 49-0924, then it can assumed that ZB belong to be a mineral mordenite group. The crystal system should be orthorhombic, lattice of end-centered, and space group of Cmc21 (36).

In this case, there are 4 possible Bravais lattice of orthorhombic crystal system i.e. simple or

primitive (P), body centered (I), end centered (C), and face centered (F) as shown in Fig. 6 [14]. There are also exist three unequal axis at right angles, $a \neq b \neq c$, $\alpha = \beta = \gamma = 90^\circ$.




Fig.6. Bravais lattice of orthorhombic.

Supandi [2] reports that crystal structure of Bayah zeolite may contains two crystal systems, there are crystal monoclinic with space group C2/m and crystal orthorhombic with space group of CmCm. Supandi conclusion based on a calculation by a refinement Rietan method.

Perhaps, the conclusion was correct, because the XRD spectrum of our sample ZB didn't merely follows the ICDD orthorhombic crystal system. Therefore, it can be assumed that our ZB sample may comprises a mixture of mineral mordenite and clinoptilolite.

Chemical Analysis

Table 6 show some metal oxide that containing in ZL and ZB as it was compared to others results.

Table 6. Metal Oxide in Zeolite

Metal Oxide	Percentage of Metal Oxide (%)			
	Current Result		*PT Minamata Clinoptilolite	*Supandi Mordenite
	ZL	ZB		
Fe ₂ O ₃	0,94	0,80	1,29	1,46
Na ₂ O	0,63	0,98	0,75	0,20
K ₂ O	0,70	0,67	1,54	2,81
CaO	0,52	0,42	1,31	2,36

*The comparison is assumed that the zeolite comes from the same area, but not exactly the same sample.

As can be seen in Table 6, the metal oxides that containing in ZL were almost nearly similar that containing in ZB. But it was not in case of the results that reported by others. The different may caused by the different of analysis method or different sample itself.

The result of Croatian zeolite of clinoptilolite was also different [16]. Therefore, the different origin of zeolite may provide different characteristics and chemical containment. For the reason, the characterization of natural zeolite became very important, before it's planned to be utilized for specific purpose.

Zeolite Filter Performance

Table 7 shows the zeolite filter performance. It can be seen in Table 7, that

Table 7. Zeolit Filter Performance

Filter	Heavy Metal Contents (gram)							
	Pb		Fe		Mg		Ca	
	X	Y	X	Y	X	Y	X	Y
Zeolit Lampung	19,07	15,33	0,49	0,43	0,28	0,24	0,94	1,02
Zeolit Banten	19,07	10,33	0,49	0,18	0,28	0,21	0,94	0,97
Activated ZL	19,07	8,86	0,49	0,26	0,28	0,22	0,94	0,84

Caution : X = before filtering, Y = after filtering.

activated ZL was found to be the best for filtering heavy metal of Pb. In this case, original solutions that contain 19.07 gr could be reduced to be 8.86 (almost 50%). On the other hand, ZL and ZB could be able to reduce only smaller i.e. it is reduces to be 15.33 and 10.33, respectively. In case of Fe, ZB shows the best as compared to that ZL and activated ZL i.e. it can reducing Fe from 0.49 gr to 0.18 gr, whereas ZL and activated ZL could reduce only 0.43 gr and 0.26 gr, respectively. All kind of zeolite (ZL, ZB, and activated ZL) was found to be worse to reduce Mg and Ca. Even more Ca became higher in case of ZL and ZB performance. The results indicate that activated zeolite became very important to design an appropriate application of natural zeolite.

4. CONCLUSION

Two types of natural zeolites i.e. originally from Lampung (ZL) and Bayah, Banten (ZB) have been characterized by XRD method. It may be concluded that ZL was belong to clinoptilolite mineral with monoclinic crystal structure and ZB was belong to mordenite mineral with orthorhombic crystal structure.

The ZB however may have a mixture composition of mordenite and clinoptilolite mineral. The chemical activation of natural zeolite was important to improve the performance of zeolite.

Different origin and different sample of zeolite provide different zeolite character. Therefore the caharacterization of natural zeolite became very important for further design application of zeolite.

ACKNOWLEDGMENT

The authors gratefully acknowledge the financial support that provide by the University Research Council (Lemlit) UIN Jakarta. Acknowledgment is also directed to Mr. Maryoto, senior technician of Center for Integrated Laboratory (PLT) UIN for assistant in chemical analysis, Ms. Nita for sample preparation, and Mr. Sugianto, Director PT Minatama for supplying zeolites. Special thank go to Dr. Jaenal for fruitful discussion.

REFERENCES

1. Thamzil Las, Husen Zamroni. (1999) *Penggunaan Zeolit dalam Bidang Industri dan Lingkungan Hidup, disajikan dalam Seminar*

- Ikatan Zeolit Indonesia (IZI)*, 14 September 1999, Jakarta.
2. Supandi (1999) *Karakterisasi Struktur Zeolit Alam Bayah Menggunakan Program Rietan (Thesis Magister Sciences)*, Program Pascasarjana, Universitas Indonesia, Prodi Material Sciences Jakarta.
 3. Xiaochun Xu, Weishen Yang, Jie Liu, Liwu Lin, Norbert Stroh, Herwig Brunner. (2004) *Synthesis of NaA Zeolite Membrane on a Ceramic hollow Fiber*, *Journal of Membrane science* 229, p.81-85.
 4. P. Worathanakul, and P. Kongkachuichay. (2008) *New SUZ-4 Zeolite Membrane from Sol-Gel Technique*, *International Journal of Chemical and Biomolecular Engineering* 1:3.
 5. Valentine Valtcher. (2009) *Veryfied Synthesis of Zeolite Materials: Preparation of Zeolite Membrane*, Universite de Haute Alsace, France. http://www.iza-online.org/synthesis/VS_2ndEd/Membrane.htm (05/26/2009 12:41 PM).
 6. Jie Liu, Xiao Bo CHEN, Wei Shen YANG, Ai Sheng HUANG, Li Wu LIN. (2002) *Preparation of Zeolite-metal Composite Membrane*, *Chinese Chemical Letters* Vol. 13, No. 2, pp 183-184.
 7. Berrin Tansel. (2008). *New Technologies for Water and Wastewater Treatment: A Survey of Recent Patents*. *Recent Patents on Chemical Engineering*, 1, p.17-26.
 8. V. Stankov-Jvanovic, T. Pecev, V. Mitic, J. Perovic, B. Jovanovic. (2003). *Natural Zeolite Application in Textile Wastewater Treatment*. *Journal of Environmental Protection and Ecology*, 4, No.3, p.700-703.
 9. Drew Chemical Corporation (1967). *Water Pretreatment*, United States, Filler Corporation, New Jersey.
 10. Dr. Ir. Kaseno. M.Eng. (1999) *Teknologi Membran: Prinsip Dasar Pembuatan dan Aplikasi, Workshop Nasional Pengembangan Teknologi Membran dan Aplikasinya di Indonesia*, 31 Agustus 1999, BPPT, Jakarta, Indonesia.
 11. Ir. Hadiati B. Haryono. (1999) *Overview Perkembangan Teknologi membran di Indonesia, Workshop Nasional Pengembangan Teknologi Membrane dan Aplikasinya di Indonesia*, 31 Agustus 1999, BPPT, Jakarta, Indonesia.
 12. Ir. Lanjar. (1999) *Keunggulan Penggunaan Membran Hibrid. Workshop Nasional Pengembangan Teknologi Membrane dan Aplikasinya di Indonesia*, 31 Agustus 1999, BPPT, Jakarta, Indonesia.
 13. Takao Kokugan. (1999) *Development of Membrane Preparation Technology in Japan. Workshop Nasional Pengembangan Teknologi Membrane dan*
 14. B.D. Cullity. (1978) *Element of X-Ray Diffraction (Second Edition)*, Addison-Wesley Publishing Company Inc., California, USA.
 15. Thamzil Las (1989) *Use of Natural Zeolites for Nuclear Waste Treatment (Ph.D. Thesis)*, The University of Salford, United Kingdom.
 16. Cerjan-Stefanović, S., Siljeg, M., Bokić, L., Stefanović, B., and Koprivanac, N. (2004). *Removal of Metal-Complex Dyestuffs by Croatian Clinoptilolite*, 14th International Zeolite Conference, 25-30 April 2004, Cape Town, South Africa.